

Structural acoustic engineered wooden flooring technical data sheet wood element

November 2022 to check if you have our latest sheet visit tier-global.com/download



Description	Tongue and groove engineered plank with a REGUPOL acoustic layer bonded within for superior coverings on a range of subfloor surfaces
Wood species:	European Oak, prime/rustic
Finish:	White oak
Approval:	FSC 100%, anti-slip
Lengths:	Random 450–2400mm (average 1800–2400mm)
Profile:	Tongue and groove on all edges, and 1mm bevel to long sides.
Finished:	Filled and sanded P120 / bespoke finish
Construction:	16mm–4mm Oak wear layer, 9mm multi-layer Birch plywood and 3mm Regupol Sonus 3 Eco acoustic centre layer (18db reduction)
Construction:	21mm–4mm Oak wear layer, 12mm multi-layer Birch plywood and 5mm REGUPOL sonus core 5 (formerly known as Regupol 7210C) acoustic centre layer (16db reduction)
Construction:	22mm–4mm Oak wear layer, 12mm multi-layer Birch plywood and 6mm REGUPOL sonus 3912 (formerly known as Regupol 3912) acoustic centre layer (16db reduction)
Lamination:	Hydraulic cold press
Glue line:	D4 moisture curing polyurethane adhesive
Norm:	DIN EN 13489: 2002 Multilayer Flooring
Reaction to fire:	Dfls1
Density:	685 Kg/m ³ 370-720 Kg/m ³ acoustic content (see below specific sheets)

Formaldehyde emissions:	Class E1 zero emissions
Warmth conduction:	15mm-0.091 W/m ² K (Please refer to additional REGUPOL® readings below)
Site conditions:	45–65% relative humidity and 18–20°C room temperature – where Underfloor heating is used, do not exceed 27°C
	Good resistance to UV, chemicals, weather conditions, aging and plasticisers
Temperature resistance:	-40 °C to +110°C

Installation method: All new access floors should be installed to SR1 standard. Pedestals must be adjusted and levelled to eliminate any rocking or lipping of the raised access panel. The locking nut on the pedestal should be utilised to avoid any opportunity of the pedestal moving during its lifespan. Where possible, the access panels should be fixed to the pedestal. If this is not possible as with some brands, SR1 standard must be achieved. See our 'Tier tips' in our full Installation and maintenance guidelines to ensure a perfect installation.

Bond with MS Polymer as per adhesive manufacturer's instructions. To ensure maximum floor strength, lay boards in a brick pattern, leaving 300mm minimum between end joints. Where spanning of joists is required, use structural 22mm+ Regupol layer and a span of 600mm centres or under. Please take exact advice per project from our specialist team.

Underfloor heating: This product is compatible with underfloor heating. Temperature resistances listed above.

Cleaning method: Ensure you use the correct Tier Global cleaning materials. Please check our website for the correct cleaning solution to use on TIER acoustix floors. Do not clean wood flooring with water alone as this will create a high risk of surface coating failure. Clean away any residues on the floor quickly.

Tier Global (UK) Limited reserves the right to modify the content of technical data sheets without prior notice.

Guarantee:

Tier Global (UK) Ltd guarantees to investigate any complaints reported within 10 years from the date of sales invoice. In the event of a valid claim, Tier Global Ltd will provide replacement materials free of charge.

The lifetime of our guarantee covers the structural integrity of the product being the production, dimensions and grading of the timber element of the board. For pre-finished floors our guarantee also covers the surface finish will adhere correctly to the boards and will not wear through for general residential use, when a preventative cleaning and maintenance program is in use.

Wood is a natural product and will expand and contract throughout the four seasons, during these seasons you may experience some natural movement which is not a product defect and is not covered by this guarantee.

As a general guideline, the ambient room temperature should be maintained between 15 and 25°C and humidity levels between 45 and 65%. To maintain these humidity levels we would recommend using a humidifier/dehumidifier. Our guarantee is subject to your room conditions being maintained in accordance with British Standards 8201 current recommendations.

Tier Global (UK) Limited maintenance products should be used to maintain the warranty (samples available).

All complaints are to be reported in writing by post or email to info@tierglobal.com within 48 hours of the issue becoming visible, to allow us to investigate the cause and extent of the problem. Our guarantee is subject to our terms and conditions.



The mark of responsible forestry



Description Regupol Sonus 3 Eco is a tough, resilient, low cost acoustic underlay that has been developed to attenuate impact sound beneath a wide range of floor finishes, including carpet, wood, laminates and tiles in concrete construction. Regupol Sonus 3 Eco is not recommended for use in timber constructions. Extremely durable, flexible and sustainable, Regupol Sonus 3 Eco delivers cost effective impact sound insulation and is ideal for all types of developments.

Benefits Designed for use with a wide range of floor finishes, including carpet and tiles as well as wooden based floor finishes, e.g. parquet

Offers long term performance without collapse or “bottoming” out under high point loads

Resistant to ageing and deformation

Zero global warming potential (GWP) and zero ozone depletion potential (ODP)

Product manufactured using Recycled Materials and 100% recyclable

Applications Regupol Sonus 3 Eco is popular with developments where effective sound control is essential and budgets must be kept to a minimum. These include:

- Apartments
- Education developments
- Hotels
- Commercial developments
- Leisure developments

Physical information

Material thickness: 3mm and 4.5mm

Material construction: Rubber/cork

Technical data

Density: approx 470kg/m3

Tensile strength (DIN 53571): approx 0.6N/mm2 (3mm thick)

Elongation at break (DIN 53571): approx 18%

Temperature resistance: -40°C to +110°C

Thermal conductivity: approx 0.085W/mk

Impact sound insulation ΔLW: 17dB

Point load tested using the Rodac RQPPA In conformity with the machinery Directive 2006/42/EC to 8kN using a 30mm diameter press tool.

Tested for efficiency and compatibility with under floor heating and using the DEVICell System with the 25mm structural board.

N.B. Below are the test times and temps, for both heat up and cool down periods. Please note these temps were taken on a Laboratory sample floor surface, so heat loss overall would be higher, in comparison to a fully fitted and sealed floor situation.

Date						
26/09/2022						
Heat Up	Time	Start Temp 16c	Temp	Cool Down	Start temp	Temp
	12.25 pm	16c		1.15 pm	19/19.5c	
	12.30 pm		16c	1.20 pm		19c
	12.35 pm		16c	1.25 pm		19c
	12.40 pm		17c	1.30 pm		19c
	12.45 pm		17c	1.35 pm		19c
	12.50 pm		17c	1.40 pm		19c
	12.55 pm		18c	1.45 pm		19c
	1 pm		18c	1.50 pm		19c
	1.05 pm		19c	1.55 pm		19c/18C
	1.10 pm		19c			
Intermittant between 19 & 19.5d	1.15 pm		19/19.5c			

Tier Global (UK) Limited reserves the right to modify the content of technical data sheets without prior notice.